









**UT.MAKAI**

<b>FORMATO/ FORMAT</b>	60X120
<b>ESPESOR/ THICKNESS (mm)</b>	10,5
<b>PRODUCTO/ PRODUCT</b>	PORCELANICO/ PORCELAIN
<b>TIPO/ KIND</b>	ESMALTADO/ GLAZED
<b>GRUPO/GROUP</b>	B1a - GL

**NORMA APLICABLE EN 14411 ANEXO G**  
**APPLICABLE STANDARD ISO 13006 ANNEX G**



ENSAYOS/ TESTS		RESULTADOS/ RESULTS	
	UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY	DIMENSIONES DIMENSIONS	CUMPLE CON LA NORMA COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA UNE-EN ISO 10545-3 WATER ABSORPTION	VALOR MEDIO (%) AVERAGE VALUE (%)	≤ 0,5 %
	UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN UNE-EN ISO 10545-4 MODULUS OF RUPTURE	FUERZA DE ROTURA BREAKING STRENGTH (N) RESISTENCIA A LA FLEXIÓN MODULUS OF RUPTURE (N/mm <sup>2</sup> )	1.600 - 2.400 N 35 - 45 N/mm <sup>2</sup>
	UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO UNE-EN ISO 10545-9 THERMAL RESISTANCE	RESULTADO RESULT	RESISTE RESISTS
	UNE-EN-ISO 10545-11 RESISTENCIA AL CUARTEO UNE-EN-ISO 10545-11 CRAZING RESISTANCE	RESULTADO RESULT	RESISTE RESISTS
	UNE-EN ISO 10545-12 RESISTENCIA A LA HELADA UNE-EN ISO 10545-12 FROST RESISTANCE	RESULTADO RESULT	RESISTE RESISTS
	UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA UNE-EN ISO 10545-13 CHEMICAL RESISTANCE	CLORURO AMÓNICO AMMONIUM CHLORIDE 100 g/l HIPOCLORITO SÓDICO SODIUM HYPOCHLORITE 20 mg/l ÁCIDO CLORHÍDRICO HYDROCHLORIC ACID 3% ÁCIDO CÍTRICO CITRIC ACID 100 g/l HIDROXIDO POTÁSICO POTASSIUM HYDROXYDE 30 g/l	A A CUMPLE CON LA NORMA COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS UNE-EN ISO 10545-14 STAIN RESISTANCE	ÓXIDO VERDE EN ACEITE LIGERO GREEN AGENT IN LIGHT OIL SOLUCIÓN ALCOHÓLICA DE YODO IODINE SOLUTION IN ALCOHOL OLIVE OIL	5 5 5

OBSERVACIONES:

VºBº LABORATORIO:

